

# Engobes – Cone 10

	Vitreous Slip Base	White Slip	Ochre Slip	Brown Slip	Black Slip
06 White Casting Slip	76	76	76	76	76
Nepheline Syenite	6.5	6.5	6.5	6.5	6.5
Gerstley Borate	8.5	8.5	8.5	8.5	8.5
Dolomite	4.5	4.5	4.5	4.5	4.5
Barium Carbonate	4.5	4.5	4.5	4.5	4.5
Additions:					
Zircopax		19			
Rutile			38		
Red Iron Oxide			0.75	7	7.5
Black Stain					19
	Green Slip	Olive Slip	Light Blue Slip	Purple Slip	
06 White Casting Slip	76	76	76	76	
Nepheline Syenite	6.5	6.5	6.5	6.5	
Gerstley Borate	8.5	8.5	8.5	8.5	
Dolomite	4.5	4.5	4.5	4.5	
Barium Carbonate	4.5	4.5	4.5	4.5	
Additions:					
Zircopax	0.75		7.5		
Rutile		2.25			
Red Iron Oxide			0.75		
Cobalt Carbonate	0.75	0.75	4.5	5.5	
Copper Carbonate	0.75				
Nickle Oxide		2			
Chrome Oxide	0.75	0.75			

	Bringle White Slip	Bringle Bright Blue Slip	Bringle Rust Brown Slip	Senska Slip	Porter White Crackle Slip
Nepheline Syenite					8
Feldspar	25	25	25	25	21.2
Ball Clay	20	20	20	20	2.2
Kaolin	20	20	20	25	44.6
Silica	30	30	30	20	24
Borax	5	5	5	5	
Whiting				5	
Bentonite					3.5
Zircopax	7.5				
Cobalt Carbonate		2.5			
Red Iron Oxide			25		

	<b>Bringle Earthy Blue Base</b>	<b>Bringle Rusty Yellow Slip</b>	<b>Bringle Orange Slip</b>	<b>Basic White Crackle Slip</b>	<b>Komive Bright White Slip</b>
Nepheline Syenite				25	
Feldspar	25	25	25		
Ball Clay	20	20	20	25	
Kaolin	20	20	20	25	50
Silica	30	30	30	25	50
Borax	5	5	5		
Bentonite					3.5
Cobalt Carbonate	1.5				
Chrome Oxide	2				
Rutile		20	20		
Red Iron Oxide		10			

	<b>Rutile Iron Slip</b>	<b>Davidson Albany Oil Spot</b>	<b>Yellow Ochre Slip</b>	<b>Patties Black Slip</b>	<b>Basic White Slip</b>
Feldspar	25				25
Nepheline Syenite				26	
Ball Clay	25			21	8.4
Kaolin	25			21	33.3
Silica	25			32	33.3
Clay Body			50		
Rutile	25				
Red Iron Oxide	50			12	
Albany Clay		80			
Yellow Ochre		20	50		
Manganese Dioxide				8	
Copper Carbonate				4	

	<b>Voukos Slip</b>	<b>Voukos Red Slip</b>	<b>Voukos Blue Slip</b>	<b>Voukos Copper Red Slip</b>	<b>Voukos Green Slip</b>
Nepheline Syenite	25	25	25	25	25
Ball Clay	20	20	20	20	20
Kaolin	20	20	20	20	20
Silica	30	30	30	30	30
Borax	5	5	5	5	5
Rutile					
Red Iron Oxide		60			
Cobalt Carbonate			2		
Copper Carbonate				2	
Chrome Oxide					3