

Black Glazes – Cone 06

Brainy Black cone 04 ox/

G-200.....	30
Whiting.....	11
Zinc ox.....	5
Gerstly Borate.....	10
Frit 3124.....	19
E.P.K.....	10
Barium carb.....	15
Add: Manganese di.....	6%
Copper carb.....	5%
RIO.....	2%
Chrome ox.....	1%

Breaks into brainy segments when applied th
Matte, Opaque.

Bronze Copper cone 01

Nephy Sy.....	15
Soda Ash.....	5
E.P.K.....	20
Manganese diox.....	40
Copper carb.....	10
Frit 3289.....	10

#20 Satin Matt (Utah)

Colemanite	50
Lithium Carb.	14
Barium Carb.	17
China Clay	12
Flint	7
* Black:	
15% Iron + 1% Nickel	

C-04 Black Gloss	
White Lead---	61
Frit 3110---	18
S ₂ O---	21
Mang Diox---	10
CMC---	1

Ken's Low-Fire Glaze (Cone 04)	
Gerstley Borate	17.40 %
Frit 3110 (Ferro)	69.56
6 Tile Clay	13.04
	100.00 %
Black	
Black stain	10.00 %
Medium to Dark Yellow	
Yellow stain	6.00-10.00 %
Strong Purple	
Pansy Purple stain	6.00-10.00 %
Medium Green	
Chrome Oxide	1.00 %
Copper Carbonate	3.00 %

Dark Opaque Glaze (Cone 06)	
Frit 3134 (Ferro)	88.8%
Georgia Kaolin	11.2
	100.0%
Add: Cobalt Oxide	3.0%
Copper Carbonate	6.0%
Zircopax	10.0%

Slate Black Glaze (Cone 06)	
Magnesium Carbonate	13.0%
Frit 14 (Hommel)	74.0
Georgia Kaolin	13.0
	100.0%
Add: Chrome Oxide	5.0%
Cobalt Oxide	1.0%
Copper Oxide	3.0%
Iron Oxide	4.0%

M&B METALIC BLACK 04	
LITHIUM CARB.	50.00
COPPER CARB.	50.00

Crane's Glossy c05 (K)

Borax	50
Colemanite	50
Rutile	10
Black Cop. Ox.	5

Yellow Ochre and Iron Glaze Cone 03

Lithium Carbonate	29.0%
Kaolin	14.0
Silica (Flint).....	57.0
	100.0%
Add: Red Iron Oxide.....	9.6%
Yellow Ochre.....	9.6%
Bentonite.....	3.0%

This glaze has a tendency to run.

Black Glaze Cone 03

Nepheline Syenite	77.4%
Frit 3130 (Ferro).....	17.3
Ball Clay	5.3
	100.0%
Add: Manganese Dioxide.....	33.3%
Bentonite.....	5.0%

BRONZE/BLACK (Cone 02)

Frit 3110 (Ferro)	9%
Copper Carbonate	18
Manganese Dioxide	73
	100%

This works best when brushed on very thin,
and fired in a gas kiln.