

Gold Glazes – Cone 06

Inglaze luster recipes for raku

Brass/Silver	
Frit "J" (Kawabata) 100% 94%	
Silver Sulfide	2
Tin Oxide (as a binder).....	2
Bentonite	2
	100%
Neon Green	
Frit "J"	96.0%
Silver Sulfide	2.0
Bentonite	2.0
	100.0%
Add: Chrome Oxide	0.2%
Gold	
Frit "J"	96.0%
Silver Sulfide	3.0
Copper Carbonate	0.5
Red Iron Oxide	0.5

	Randall Bruce Luster - CM	Dayman's S-L's Silver	John Buck Luster #1	John Buck Luster #2	John Buck Luster #3	John Buck Luster #4
F-3110	90					
OM-4	10					
Gerstley Borate		75	87	74	50	26
Nepheline Syenite		20	13	12		
EPK		5				
Silica				14	17	32
Grolleg					33	12
Borax(dehydrated)						8
Soda ash						22
Bismuth Subnitrate	2		4.5	4		1
Silver Nitrate	1	1	4.5	4	1.7	1
Tin Oxide			2.25			
	Bisque ware to C08, then apply glaze with a brush. Fire to C08, and put kiln into post fire reduction with sugar cubes until kiln color is gone.					
					#3 and #4 are sensitive to too much reduction	Nitrates will fume away if they are fired for a long time in the kiln.

Blue Silver Raku Glaze	
Lithium Carbonate	9.8%
Frit 25 (Pemco)	42.5
Frit 3134 (Ferro)	27.4
Edgar Plastic Kaolin	6.3
Flint	14.0
	100.0%
Add: Soda Ash	1.0%
Bentonite	2.0%
Cobalt Carbonate	1.1%
Silver Nitrate	2.1%

RAKU #8 GOLD LUSTER	
Colmanite	40.00
Sorax	50.00
Silica Flint	10.00
	100.00
Add: Silver nitrite	.5%

GEORGE'S GOLD AUB
 FRIT 3195 → 90
 BISMUTH SUBNITRATE → 4
 BALL CLAY → 10
 SILVER NITRATE → 1
 105 gms.

Raku Glazes

Gold Lusters