

Raku Clay Bodies

Raku Body I	
A.P. Green Fireclay	90 parts
Tennessee Ball Clay (SGP 1)	15
Wollastonite (F-1)	5
Kyanite (raw, 35 mesh)	15
Grog	10
	<hr/> 135 parts
Raku Body II	
A.P. Green Fireclay	200 parts
Ball Clay (Bandy Black)	50
Ball Clay (C&C)	50
Saggar Clay	100
Pyrophyllite (Pyrotol)	50
Grog	50

G. TIMOCK - 1986	
CLAY raku cone 04	
Fireclay	40lbs.
Ball Clay	10
Talc	20
Cedar Heights Gold Art.	15
10 mesh Grog	25
Chopped Nylon Fiber	1/2

TIMOCK'S RAKU CLAY BODY

FIRECLAY (CHIC. WELLSVILLE)	→ 40
HAWTHORNE BOND FIRECLAY	→ 10
BALL CLAY	→ 20
TALC (PRE-MIX WATER)	→ 20
9 MESH GROG	→ 50
NYLON FIBER (CHOPPED)	→ 1/2 lb.

Lawton Raku Body	
Talc	15.0 parts
Kyanite (35 mesh)	15.0
Spodumene	10.0
A. P. Green Fireclay	55.0
Bentonite	0.5
Kentucky Ball Clay (OM 4)	10.0
XX Saggar Clay	5.0
	<hr/> 110.5 parts

J. ROMBERG'S RAKU BODY	
Lincoln Fireclay	50
Talc	20
70 mesh Sand	12
30 mesh Sand	12
Ball Clay	10
Grog	8

Raku Body	
Talc	15%
A. P. Green Fireclay	20
Georgia Kaolin (6 Tile)	20
Kentucky Ball Clay (OM 4)	15
XX Saggar Clay	15
Silica Sand	15
	<hr/> 100%

Wayne Higby's white raku clay	
Missouri fire clay	100 lb
OM 4 ball clay	30 lb
Talc	30 lb
Silica sand	10 lb
Macaloid	1%

Wayne Higby's red raku clay	
PBX fireclay	50 lb
Goldart	20 lb
Redart	25 lb
Talc	5 lb
Silica sand	10 lb
Macaloid	1%